



## TECHNICAL DATA SHEET

## FAST DRYING ALKYD ANTIRUST

Name:	ALKYCOL PRIMER
Code:	101.00000
Color:	WHITE, GRAY, IVORY, OXIDE RED, GREEN, BLACK
Appearance:	OPAQUE
Packaging:	KG 25 TIN
Availability:	IN STOCK

Specific thinner: **SYNTETHIC**

Name: SYNTETHIC DILUENT

Code: 800.93405

### WHERE TO USE

Fast-drying alkyd primer for properly prepared iron supports. The product is oversprayable by synthetics, chlorinated rubber and nitroindustrial products. Particularly suitable for protecting farm machines, trailers, plows and construction equipment such as concrete mixers and nerds from rust. The recommended minimum final thickness is not less than 60µm in dry film.

### CHEMICAL AND PHYSICAL CHARACTERISTICS

1

#### Referred to the undiluted one-component product

The physical constants are indicative and subject to normal production tolerances in accordance with ISO 3534-1. The data shown are relative to the White Color. For different colors the physical constants can take different values.

Calculated specific weight	Kg/L 1.350 ± 0.020 L/Kg 0.730 ± 0.020
Fineness of grinding	>6 Hegman scale (NS)
Calculated dry residue	Weight 63% ± 2% Volume 44% ± 2%
Binder	ALKYD
C.O.V.	< 500 g/L
Calculated theoretical yield* 35µm dry film	8.8 mq/Kg 12.0 mq/L





## TECHNICAL DATA SHEET

\* The yield must be evaluated from time to time, as it is conditioned by multiple external and environmental factors that are variable during the application phase. In estimating the quantities necessary for the execution of the work, it is also necessary to consider the possible losses of material during mixing and application.

Drying	Air T° 25°C Relative humidity 70%
Dust out	15' - 30'
Dry to the touch	1 hour
Dry in depth	2 days
Overpainting	after 1 hour

## APPLICATION INSTRUCTIONS

2

### Optimal conditions for the application

Temperature not lower than 5°C, and anyway when the T° of the surface is at least above dew point.

Relative humidity not exceeding 80%.

Note: Excessive moisture or condensation during polymerization can negatively interfere with the polymerization itself and / or cause discoloration. Above or below normal conditions it may be necessary to use special application techniques and particularly dilution ratios.

### How to treat the surface

The surface must be clean and dry. A suitable method must be used to remove dirt, dust, oils and other contaminants that could interfere with the adhesion of the product.

#### Less complex procedure:

Perform an accurate degreasing as indicated in the SSPC-PC 1-63 specification. Alternatively, you can proceed with mechanical St2 grade brushing as indicated in the SSPC-SP3 specification.

#### More complex procedure:

Sandblast up to Sa 2½ grade as indicated in the SSPC-SP 10-63T specification and proceed with the application of the product within 6 hours.

Note: After each surface preparation operation, an accurate blowing must always be carried out using dehumidified compressed air as indicated in the ISO 8573 standard.



Via Giorgio Ambrosoli 10/12 50136 Florence - Italy  
Phone: +39 055 6503108 - Fax: +39 055 9900125  
VAT Number 00433270485  
[www.colgom.com](http://www.colgom.com) - [colgom@dada.it](mailto:colgom@dada.it)



## TECHNICAL DATA SHEET

### Mode

By spray	SUITABLE
By roller	SUITABLE
By brush	SUITABLE
Note: Taking care to reach the required thickness	

### MIXTURE AND DILUTION

Both depend on the application method.

The use of a diluent other than the specific one indicated may have a negative effect on the behavior of the coating applied, with the cancellation of guarantees also explicitly expressed and / or agreed upon.

Note: Carefully mix the product before dilution. Adding the thinner and mix again.

#### Spray application

With AIRLESS and AIRMIX systems, dilute up to the viscosity of 40" Ford Cup No. 4 at 20°C.

On request the product is available for application with ELECTROSTATIC system. If applied with a preheater, adjust the temperature to 40°C with 50" viscosity Ford Cup No. 4 at 20°C. It is recommended to reach the required thickness.

#### Roller application

Maximum dilution 5%, taking care to reach the required thickness.

#### Brush application

Maximum dilution 5%, taking care to reach the required thickness.

### INSTRUCTIONS FOR STORAGE

The product must be stored in accordance with national regulations. After the indicated period of time, check before use to verify the integrity of the product. Storage at high temperatures significantly reduces the period of use of the product.

#### Primer

12 months from the date of production in sealed can, as long as the material is placed indoor, away from heat sources, protected from frost and anyway within the limits of 4 - 30°C and humidity 0 - 80%.





## TECHNICAL DATA SHEET

### HEALTH AND SAFETY

To be used exclusively for the uses and conditions shown on this data sheet.

In applications it is always necessary to provide adequate room ventilation.

Do not inhale the nebulised paint. Do not eat, drink or smoke during use. Do not disperse into environment. Collect spillages.

Dispose of the product / container in accordance with national regulations.

The product causes serious eye irritation. Wearing protective gloves / clothing. Protecting eyes / face. In case of contact with the skin, removing the paint with a suitable detergent, soap and water. Keep out of reach of children.

**In case of need, consulting Niguarda Hospital's venoms Center at the number 02/66101029**

For detailed information on health and safety hazards and precautions for the use of this product, always consult the Safety Data Sheet.

#### Please Note:

Since the conditions of use of our materials are not under our direct control, we decline any responsibility for the improper use that is made of them, for the direct or indirect damages that can derive from their use towards anyone and for the duration in time of the product after its application.

Colgom© does not assume any responsibility, of any kind, implicit or explicit, whether imposed or requested by the client, or otherwise indicated, also with reference to the covering power and suitability for a particular use or service, also with reference to the covering power and suitability for a particular use or service, unless otherwise written agreed in writing between the Parties. Colgom© ensures that all its products are manufactured according to established procedures and their final quality complies with the standards set by its quality control.

Colgom© reserves the right to change the information given without prior notice.

#### Revision N.01/2019

This data sheet replaces all the previous ones.





TECHNICAL DATA SHEET

---



Via Giorgio Ambrosoli 10/12 50136 Florence - Italy  
Phone: +39 055 6503108 - Fax: +39 055 9900125  
VAT Number 00433270485  
[www.colgom.com](http://www.colgom.com) - [colgom@dada.it](mailto:colgom@dada.it)