



ALUMINIZED BITUMINOUS EPOXY ENAMEL

Name: VYNIL BITUMINOSA COLGOM COAT
Code: 999.00565
Color: ALUMINUM, SIMILAR TO RAL 9006
Appearance: SATIN
Packaging: KG 25 TIN
Availability: ON REQUEST

Specific thinner: [SYNTETHIC](#)
Name: SYNTETHIC DILUENT
Code: 800.93405

WHERE TO USE

Waterproofing enamel, with bituminous layers, made for painting flat and curved cover. The aluminum reflective effect no leafing reduces the absorption of solar radiations favoring the lowering of the roof covering temperature, in addition to guaranteeing a longer duration of the covering itself.

CHEMICAL AND PHYSICAL CHARACTERISTICS

Referred to the undiluted one-component product

The physical constants are indicative and subject to normal production tolerances in accordance with ISO 3534-1.

Calculated specific weight	Kg/L 0.990 ± 0.020 L/Kg 1.000 ± 0.020
Calculated dry residue	Weight $40\% \pm 2\%$ Volume $38\% \pm 2\%$
Binder	SPECIAL BITUMENS + VINYL
C.O.V.	< 500 g/L
Calculated theoretical yield* two applications	7.3 mq/Kg 7.4 mq/L



TECHNICAL DATA SHEET

* The yield must be evaluated from time to time, as it is conditioned by multiple external and environmental factors that are variable during the application phase. In estimating the quantities necessary for the execution of the work, it is also necessary to consider the possible losses of material during mixing and application.

Drying	Air T° 25°C Relative humidity 70%
Dry to the touch	2 hours
Dry in depth	after 4 days
Overpainting	after 2 hours

APPLICATION INSTRUCTIONS

Optimal conditions for the application

Temperature not lower than 5°C, and anyway when the T° of the surface is at least above dew point.

Relative humidity not exceeding 80%.

Note: Excessive moisture or condensation during polymerization can negatively interfere with the polymerization itself and / or cause discoloration. Above or below normal conditions it may be necessary to use special application techniques and particular dilution ratios.

How to treat the surface

The surface must be clean and perfectly dry. A suitable method must be used to remove dirt, dust, oils and other contaminants that could interfere with the adhesion of the product.

Mode

By roller	SUITABLE
By brush	SUITABLE
By spray	NOT SUITABLE



TECHNICAL DATA SHEET

MIXTURE AND DILUTION

Both depend on the application method.

The use of a diluent other than the specific one indicated may have a negative effect on the behavior of the coating applied, with the cancellation of guarantees also explicitly expressed and / or agreed upon.

Note: Carefully mix the product before dilution. Adding the thinner and mix again.

Roller application

Maximum dilution 5%, taking care to reach the required thickness.

Brush application

Maximum dilution 5%, taking care to reach the required thickness.

INSTRUCTIONS FOR STORAGE

The product must be stored in accordance with national regulations. After the indicated period of time, check before use to verify the integrity of the product. Storage at high temperatures significantly reduces the period of use of the product.

3

Enamel

12 months from the date of production in sealed can, as long as the material is placed indoor, away from heat sources, protected from frost and anyway within the limits of 4 - 30°C and humidity 0 - 80°C.

HEALTH AND SAFETY

To be used exclusively for the uses and conditions shown on this data sheet.

In applications it is always necessary to provide adequate room ventilation.

Do not inhale the nebulised paint. Do not eat, drink or smoke during use. Do not disperse into environment. Collect spillages.

Dispose of the product / container in accordance with national regulations.

The product causes serious eye irritation. Wearing protective gloves / clothing. Protecting eyes / face. In case of contact with the skin, removing the paint with a suitable detergent, soap and water. Keep out of reach of children.

In case of need, consulting Niguarda Hospital's venoms Center at the number 02/66101029

For detailed information on health and safety hazards and precautions for the use of this product, always consult the Safety Data Sheet.



Via Giorgio Ambrosoli 10/12 50138 Florence - Italy
Phone: +39 055 6503108 - Fax: +39 055 9900125
VAT Number 00433270485
www.colgom.com - colgom@dada.it



TECHNICAL DATA SHEET

Please Note:

Since the conditions of use of our materials are not under our direct control, we decline any responsibility for the improper use that is made of them, for the direct or indirect damages that can derive from their use towards anyone and for the duration in time of the product after its application.

Colgom© does not assume any responsibility, of any kind, implicit or explicit, whether imposed or requested by the client, or otherwise indicated, also with reference to the covering power and suitability for a particular use or service, also with reference to the covering power and suitability for a particular use or service, unless otherwise written agreed in writing between the Parties. Colgom© ensures that all its products are manufactured according to established procedures and their final quality complies with the standards set by its quality control.

Colgom© reserves the right to change the information given without prior notice.

Revision N.01/2019

This data sheet replaces all the previous ones.

